



Glass Bottle Firing Program

Rate (C)	Temp (C)	Hold (min)
170	510	0
250	780	10
9999 (full)	510	60
70	400	30
9999 (full)	25	0

Note:

This data is a guide only, firing programmes may need to be adjusted according to size and thickness of glass and the kiln's performance. Ensure that data is entered into the controller accurately, otherwise glass may not fuse correctly. Creative Glass Guild sells all glass, tools and materials on the basis that customers have the knowledge and ability to use them safely and in accordance with all relevant regulations and legislation.

www.creativeglassguild.co.uk

Tel +0044 (0)117 95 888 20